

AMENDMENTS TO THE CLAIMS:

Please cancel claims 3 and 9 without prejudice or disclaimer without prejudice or disclaimer.

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (Previously presented): A method of forming a luster coating film, comprising the steps of:

(1) applying an aqueous luster thermosetting base coating composition (A), the solids content of the base coating composition (A) being about 5 to about 15 wt.% to a substrate in four or five stages, in such a manner that the thickness of the base coating composition (A) applied in the first stage becomes 1 to 5 μm when cured, the thickness of the base coating composition (A) applied in each of the second and subsequent stages becomes 0.3 to 5 μm when cured, and the total thickness of the base coating composition (A) applied in all of the stages in step (1) is 10 to 15 μm when cured;

(2) applying a thermosetting clear coating composition (B) over the uncured or heat-cured coating layer of the base coating composition (A); and

(3) heating the two-layer coating comprising the base coating composition (A) and clear coating composition (B) to obtain a cured two-layer coating film;

wherein, in step (1), the solids content of the aqueous luster thermosetting base coating composition (A) one minute after the application in each stage is at least 40 wt. %; and

U.S. Patent Application Serial No. **10/576,277**
Response filed May 27, 2010
Reply to OA dated April 28, 2010

wherein, in step (1), after each coating stage, the applied composition is allowed to stand, or is preheated at about 50 to about 80°C.

Claim 2 (Original): The method according to claim 1, wherein the aqueous luster thermosetting base coating composition (A) comprises a water-soluble or water-dispersible, crosslinkable functional group-containing resin, a crosslinking agent and a flaky luster pigment.

Claims 3-4 (Canceled).

Claim 5 (Original): The method according to claim 1, wherein the substrate is an automotive body or a part thereof.

Claim 6 (Original): An automotive body or part thereof having a luster coating film formed by the method according to claim 5.

Claim 7 (Previously presented): A method of forming a luster coating film, comprising the steps of:

(1) applying an aqueous luster thermosetting base coating composition (A), the solids content of the base coating composition (A) being about 5 to about 15 wt. % to a substrate in four or five stages, in such a manner that the thickness of the base coating composition (A) applied in the first

stage becomes 1 to 5 μm when cured, the thickness of the base coating composition (A) applied in each of the second and subsequent stages becomes 0.3 to 5 μm when cured, and the total thickness of the base coating composition (A) applied in all of the stages in step (1) is 10 to 15 μm when cured;

(2) applying a thermosetting clear coating composition (B) over the uncured or heat-cured coating layer of the base coating composition (A);

(3) applying a thermosetting clear coating composition (C) over the uncured or heat-cured coating layer of the clear coating composition (B); and

(4) heating the three-layer coating comprising the base coating composition (A), clear coating composition (B) and clear coating composition (C) to obtain a cured three-layer coating film;

wherein, in step (1), the solids content of the aqueous luster thermosetting base coating composition (A) one minute after the application in each stage is at least 40 wt. %; and

wherein, in step (1), after each coating stage, the applied composition is allowed to stand, or is preheated at about 50 to about 80°C.

Claim 8 (Original): The method according to claim 7, wherein the aqueous luster thermosetting base coating composition (A) comprises a water-soluble or water-dispersible, crosslinkable functional group-containing resin, a crosslinking agent and a flaky luster pigment.

Claims 9-10 (Canceled).

U.S. Patent Application Serial No. **10/576,277**
Response filed May 27, 2010
Reply to OA dated April 28, 2010

Claim 11 (Original): The method according to claim 7, wherein the substrate is an automotive body or a part thereof.

Claim 12 (Original): An automotive body or part thereof having a luster coating film formed by the method according to claim 11.